

**PRODUCT DATA SHEET**

**AZLB-Na  
Bowie Chabazite**

Anhydrous Sodium Aluminosilicate, Natural Herschelite-Sodium Chabazite

**Zeolite Powder and Granules**

**TYPICAL PROPERTIES**

Form	Granules & Powders
Color	Reddish / Tan (dry brightness 40)
Ring Members	8
Crystal Size	Less than 1 micron
Crystallinity	+90%
Density	1.73 g/cm <sup>3</sup>
Pore Size	4.1 by 3.7 Angstroms
Effective Pore Diameter	4.3 Angstroms
Cavity Size	11.0 by 6.6 Angstroms
Total Pore Volume	.468 cm <sup>3</sup> /g
Surface Area	520 m <sup>2</sup> /g
Crystal Void Volume	.47 cm <sup>3</sup> /cm <sup>3</sup>
Packing Density	Approx. (40 - 44 lbs/ft <sup>3</sup> )
SiO <sub>2</sub> /Al <sub>2</sub> O <sub>3</sub> Ratio	Approx. 4:1
MOH's Hardness	4 - 5
Moisture as Packaged	Less than 20% by Weight
pH of 1% Dispersion	8.5
Stability	pH of 3 through 12
Ion Exchange Capacity	2.50 meq/g
Sorption Capacity	>15 wt. % H <sub>2</sub> O at 10% RH

**CONTACT INFO**

Inquiries/Sales: (203) 364-0600  
 Email: [info@stcloudmining.com](mailto:info@stcloudmining.com)


**PRODUCT DATA SHEET**

**AZLB-Na  
 Bowie Chabazite**

**TYPICAL CHEMICAL ANALYSIS (Anhydrous Basis)**

SiO <sub>2</sub>	Al <sub>2</sub> O <sub>3</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO	MgO	Na <sub>2</sub> O	K <sub>2</sub> O	Dominant Cation
68.1	18.59	2.84	0.27	0.75	8.32	1.12	Na

**EXCHANGE SELECTIVITIES**



**EXCHANGE OF HEAVY METAL IONS**

Weight Percent of Heavy Metals Retained in Anhydrous CABSORB after Ion Exchange from a .10 mg/ml solution: AgNO<sub>3</sub>, Pb(NO<sub>3</sub>)<sub>2</sub>, CoSO<sub>4</sub> and a 0.025 mg/ml solution of CuSO<sub>4</sub> at the Initial pH Indicated for each Solution

<u>Ag</u>		<u>Pb</u>		<u>Cu</u>		<u>Co</u>	
pH	Wt%	pH	Wt%	pH	Wt%	pH	Wt%
5.30	21.85	3.80	15.27	3.43	3.17	2.91	2.82

**RELATED MATERIALS**

- |                       |                  |
|-----------------------|------------------|
| Linde AW 500          | Sapo 34          |
| Linde Ion Sieve IE 95 | TSM 300          |
| Linde Ion Sieve IE 96 | 2 K – 14         |
| Linde D               | 2 YT – 6         |
| Linde R               | Acadialite       |
| LZ 218                | Haydenite        |
| MAPO 44               | Seebachite       |
| MAPO 47               | Willhendersonite |

*Information herein is accurate to the best of our knowledge. Suggestions are made without warranty or guarantee of results. Before using, user should determine the suitability of the product for his intended use and user assumes the risk and liability in connection therewith. We do not suggest violation of any existing patents or give permission to practice any patented invention without a license.*